

TEGO® Airex 991

DESCRIPTION

TEGO® Airex 991 shows very strong defoaming against both macro- and micro foam in solventborne and high solids coatings. Especially for spray-applied coatings.

KEY BENEFITS

- highly recommended for airless spraying
- highly efficient
- solvent-free

APPLICATION RECOMMENDATION

Brush application/roller application



Airless spraying



Compressed air spraying



Flexo/gravure printing



Dip coating, flow coating, curtain coating



Flooring



SUITABILITY

waterborne



solventborne



2-pack 100%



radiation-curing



pigmented coatings



clear coatings



● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Protective coatings
- High solid industrial coatings
- General industrial coatings
- Floor coatings

TECHNICAL DATA

active matter content 100 %

appearance colored liquid

chemical description formulation based on deaerating organic polymers, with a tip of silicone

SOLUBILITY

Water



Ethanol



TPGDA



Acetone



Butylacetate



Mineral Spirits



● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.3 - 1.0 %

PROCESSING INSTRUCTIONS

- Stir before use!
- Additive must be incorporated with sufficiently high shear.
- Addition as supplied is recommended.

HANDLING & STORAGE

When stored in an original unopened packaging between -10 and +40 °C, the product has a shelf life of 24 months from the date of manufacture.

MSDS & REGULATORY INFORMATION



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com