## DESCRIPTION

 $\mathsf{TEGO}^{\circ}$  Glide 450 provides excellent flow and leveling combined with strong slip properties. It is recoatable and can be used in solvent and waterborne coatings.

### **KEY BENEFITS**

- excellent leveling
- good slip effect
- recoatable

## EFFECT

Anti-crater effect		
Flow promotion		
Slip effect		
Anti-blocking		
Low foam		

### SUITABILITY

solventborne
•
radiation-curing
0
clear coatings
•

🔍 not suitable 🧖 partly suitable 🛡 suitable

#### **TYPICAL APPLICATIONS**

- Car OEM coatings
- Car repair coatings
- Wood coatings
- Plastic coatings

## **TECHNICAL DATA**

active matter content	100 %
appearance	clear liquid
chemical description	polyether siloxane copolymer

# SOLUBILITY

Water	Ethanol
0	•
TPGDA	Acetone
•	٠
Butylacetate	Mineral Spirits
•	•

### **RECOMMENDED ADDITION LEVEL**

As supplied calculated on total formulation: 0.05 - 0.7 %

### **PROCESSING INSTRUCTIONS**

- Addition to the coating as supplied or as a predilution is possible.
- Predilution in a suitable solvent simplifies dosage and incorporation.

### HANDLING & STORAGE

When stored in an original unopened packaging between -40 and +40  $^\circ\text{C}$ , the product has a shelf life of at least 36 months from the date of manufacture.

## **MSDS & REGULATORY INFORMATION**



This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described here inshold be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com

