

DESCRIPTION

AEROSIL® R 7200 is a structure modified fumed silica after treated with methacrylsilane.

KEY BENEFITS

- improves scratch resistance
- low rheological effect
- high loadings possible

GRAPHICAL BAR**Anti-settling****Anti-sagging****Scratch- and abrasion resistance****SUITABILITY****waterborne****solventborne****radiation-curing****1-pack coatings****2-pack coatings**

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

Radiation-curing coatings

TECHNICAL DATA

carbon content	4.5 - 6.5 %
loss on drying	Max. 1,5 %
pH-value	4.0 - 6.0
SiO₂ content	Min. 99.8 %
specific surface area (BET)	125 - 175 m ² /g
tamped density	Approx 230 g/l

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 5 - 20 %

HANDLING & STORAGE

The product is supplied in multiple layer 15 kg bags. We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances. The product should be used within 2 years after production.

MSDS & REGULATORY INFORMATION

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com